



DESCRIPTION AND USES

Port City Log Cabin Wood Finish is a penetrating wood finish that protects exterior wood while enhancing its natural grain and texture. The special formula of this product allows the wood to “breathe,” minimizing the risk of peeling. It also contains special pigments that impart a transparent amber color and protect against damaging UV rays. It is intended for use on vertical surfaces such as siding and fences. It is also suitable for use on exterior furniture. It is not recommended for use on horizontal surfaces such as decks. Do not use over surfaces previously stained or coated with other types of clear wood finishes or preservatives.

SPECIFICATIONS

SURFACE PREPARATION: All surfaces to be coated must be dry and clean.

New Wood: Sand new wood to remove mill glaze that will prevent the coating from penetrating. Dry brush rough wood to remove loose dirt and wood fibers.

Weathered Bare Wood: Use a wood brightener to restore wood to its natural color. Power wash this cleaning solution from the wood with plain water. Allow at least 3 days drying time after washing before finishing.

Previously Coated or Stained Wood: The old finish must be completely removed before using Port City Log Cabin Finish on these surfaces.

APPLICATION: Stir well. Do not thin. On bare wood surfaces, apply three coats, allowing 24 hours dry time between coats. Use a natural bristle brush to apply liberal coats, brushing well in the direction of the wood grain. Do not apply at temperatures below 50°F. Do not apply in direct sunlight or on hot surfaces. Clean tools after use with Paint Thinner (Mineral Spirits).

MAINTENANCE: Maintenance of surfaces coated with this product will vary depending on location, type of surface and other factors. A yearly inspection of the coated surface should be made. Small areas of peeling or flaking should be sanded to remove the failed coating and then touched up with two coats. Over time, cracks may develop in wood surfaces. Apply two coats to these cracks when they become visible. When complete re-coating becomes necessary, usually every 2-3 years, clean the surface by applying a solution made out of 4 oz. Tri-Sodium Phosphate (TSP), 1 quart household bleach, and 3 quarts water. Rinse the solution off the wood with a power washer, being careful not to damage the surface by holding the nozzle too close or using too much pressure. **Port City Log Cabin Maintenance Coat** may also be used in cases where the desired color has already been achieved with previous coats of **Port City Log Cabin Wood Finish** and no further addition of color is desired.

CLEAN UP: Clean tools and equipment immediately with Paint Thinner (Mineral Spirits).

For complete safety information, refer to the SAFETY DATA SHEET for this product.

PRODUCT CODES

5 GALLONS

00545 - Cedar
00546 - Cypress
00547 - Butternut
00548 - Mahogany

GALLONS

00549 - Cedar
00550 - Cypress
00551 - Butternut
00552 - Mahogany

QUARTS

00556 - Cedar
00555 - Cypress
00554 - Butternut
00553 - Mahogany

COMPANION PRODUCTS:

Log Cabin Maintenance Coat

TECHNICAL DATA

VEHICLE TYPE: Alkyd Resin

FINISH: Low Sheen

VOLUME SOLIDS: 43%

WEIGHT SOLIDS: 50%

DENSITY: 7.7 lbs/gal

VOC: 460 g/L

CLEAN UP SOLVENT: Paint Thinner (Mineral Spirits)

COVERAGE: 300 SF/gallon

DRY TIME: Dry to touch in 8 hours. Recoat in 24 hours.

SHELF LIFE: 1 year shelf life when properly stored.

Port City Paints
1250 9th St.
Muskegon, MI 49440
www.portcitypaints.com

The suggestions for use and technical data here given are accurate to the best of our knowledge and are offered in good faith. Because the conditions and use of our products are beyond our control, our liability, if any, is limited to the replacement of defective material only. RepcoLite Paints, Inc. DISCLAIMS ALL OTHER WARRANTIES relating to our products and DISCLAIMS ALL WARRANTIES RELATING TO THEIR APPLICATION, expressed or implied, INCLUDING but not limited to warranties of merchantability and fitness for a particular purpose. TECHNICAL DATA IS SUBJECT TO CHANGE WITHOUT NOTICE.